

## TEST REPORT


**REPORT NUMBER :** TURR150096117  
**APPLICANT NAME :** Global Kauçuk Sızdırmazlık Elemanları San.Tic.Ltd.Şti.  
**ADDRESS :** Selamet Mah. Tütüncü Sok.No:20 Bursa / TURKEY  
TEL:0545 807 26 94  
**Attention :** Melek Koni ( melekconi@globalkaucuk.com.tr )  
**SAMPLE DESCRIPTION :** One sample of EPDM 50 Black rubber  
**DATE IN :** 11 June ,2015 ( 13:45)  
**DATE OUT :**  
**MANUFACTURER'S NAME :** GLOBAL KAÜÇUK  
**REQUEST.** RoHS Test was performed according to 2011/65/EU Directive.  
**RESULTS:** See attachment

PART	DESCRIPTION	CONCLUSION
Sample 1	Sample	Pass


This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>.

The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and TÜRKAK accreditation requirements. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. When uncertainty is taken into account, the result may be borderline. Borderline results need to be re-tested to determine their disposition up to customer's decision. Opinions and interpretations expressed herein are outside the scope of TÜRKAK accreditation. Tests marked □ in this test report are not included in the TÜRKAK accreditation schedule for this laboratory.

PP



Volkan ALBAYRAK  
COORDINATOR



Neslihan Sözer  
Chemical Laboratory Manager



**(A) TEST RESULT SUMMARY ACCORDING TO IEC 62321 : 2008**
**Electrotechnical Products-Determination of Levels of Six Regulated Substances**

TESTING ITEM	RESULT
	<b>Sample 1</b>
	Part
Cadmium (Cd) Content	ND
Chromium VI (Cr+6) Content (ppm) (for non- metal)	ND
Chromium VI (Cr+6) Content ( $\mu\text{g}/\text{cm}^2$ ) (for metal)	NA
Chromium VI (Cr+6) Result (By spot test on metal)	NA
Lead (Pb) Content	ND
Mercury (Hg) Content	ND
Flame Retardants	
<b>Polybrominated Biphenyls (PBB)</b>	ND
Monobromobiphenyl (MonoBB)	ND
Dibromobiphenyl (DiBB)	ND
Tribromobiphenyl (TriBB)	ND
Tetrabromobiphenyl (TetraBB)	ND
Pentabromobiphenyl (PentaBB)	ND
Hexabromobiphenyl (HexaBB)	ND
Heptabromobiphenyl (HeptaBB)	ND
Octabromobiphenyl (OctaBB)	ND
Nonabromobiphenyl (NonaBB)	ND
Decabromobiphenyl (DecaBB)	ND
<b>Polybrominated Diphenyl Ethers (PBDE)</b>	ND
Monobromodiphenyl Ether (MonoBDE)	ND
Dibromodiphenyl Ether (DiBDE)	ND
Tribromodiphenyl Ether (TriBDE)	ND
Tetrabromodiphenyl Ether (TetraBDE)	ND
Pentabromodiphenyl Ether (PentaBDE)	ND
Hexabromodiphenyl Ether (HexaBDE)	ND
Heptabromodiphenyl Ether (HeptaBDE)	ND
Octabromodiphenyl Ether (OctaBDE)	ND
Nonabromodiphenyl Ether (NonaBDE)	ND
Decabromodiphenyl Ether (DecaBDE)	ND

Remarks : ppm=Parts per million based on dry weight of sample  
 $\mu\text{g}/\text{cm}^2$ =Microgram per square centimetre  
 mg/kg with 50  $\text{cm}^2$ =Milligram per kilogram with 50 square centimetre  
 ND =Not detected NA =Not applicable NR =Not requested



**TEST REPORT**

17 June ,2015

REPORT : TURR150096117

Page 3 of 4

**(B) REQUIREMENT:**

SUBSTANCE	LIMITS
Cadmium (Cd) Content	0.01 % (100 ppm)
Chromium VI (Cr+6) Content (ppm) (for non metal)	0.1 % (1000 ppm)
Chromium VI (Cr+6) Content ( $\mu\text{g}/\text{cm}^2$ ) (for metal)	
Chromium VI (Cr+6) Result (By spot test on metal)	NEGATIVE
Lead (Pb) Content	0.1 % (1000 ppm)
Mercury (Hg) Content	0.1 % (1000 ppm)
Flame Retardants	0.1 % (1000 ppm)

**(C) TEST METHOD :**

Testing Item	Testing Method	Reporting Limit
Cadmium (Cd)Content	With reference to IEC 62321:2008,by acid digestion and determined by ICP-OES	2 ppm
Lead (Pb)Content	With reference to IEC 62321:2008,by acid digestion and determined by ICP-OES	2 ppm
Mercury (Hg)Content	With reference to IEC 62321:2008,by acid digestion and determined by ICP-OES	2 ppm
Chromium VI (Cr6+) (For non-metal)	With reference to IEC 62321:2008,by alkaline digestion and determined by UV-VIS spectrophotometer	1 ppm
Chromium VI (Cr6+) (For metal)	With reference to IEC 62321:2008,by SPOT TEST	1 ppm (IN TESTING SOLUTION)
Chromium VI (Cr6+) (For metal)	With reference to IEC 62321:2008 ,by boiling water extraction and determined by UV-VIS spectrophotometer	0.02 mg/kg with 50 cm <sup>2</sup> (IN TESTING SOLUTION)
PBBs/PBDEs	With reference to IEC 62321:2008,by solvent extraction and determined by GC/MS and HPLC	5 ppm



Sample 1



#### END OF TEST REPORT ###

